

# Product portfolio for Herbarium application



	Measurement item	Unit	X-32-3808	X-32-3823	X-32-3863
Uncured properties	Appearance A	-	Transparent	Transparent	Translucent
	Appearance B	-	Transparent	Transparent	Transparent
	Viscosity A at 23°C	mPa · s	100	630	900
	Viscosity B at 23°C	mPa · s	60	500	330
	Density A at 23°C	g/cm <sup>3</sup>	0,97	0,97	0,99
	Density B at 23°C	g/cm <sup>3</sup>	0,97	0,97	0,98
	Mix ratio	-	100 : 100	100 : 100	100 : 100
	Pot-life at 23°C	min	300	17	24
	Cure time at 23°C	min	1440	60	70
	Cured properties	Hardness Shore A	-	17	27
Elongation at break		%	70	80	100
Tensile strength		MPa	0,3	0,5	3,0

Not specified values